



DESCRIPTION

A premium alkyd high-gloss enamel for use on properly prepared wood, metal or masonry surfaces. Provides a hard shiny finish which is typical of premium alkyd paints. The fast dry formula allows for recoat in two hours which improves your painting productivity. Use for residential, commercial and light industrial applications.

FEATURES

- ▶ Durable gloss finish
- ▶ Fast Drying
- ▶ Good Abrasion Resistance
- ▶ Good resistance to oil, grease and water
- ▶ Good color and gloss retention
- ▶ Easy Application
- ▶ Humidity regulating

COMPOSITION

- ▶ Alkyd Resin
- ▶ Titanium Dioxide and Extender Pigments
- ▶ Not manufactured with lead or chromate containing materials

SPECIFICATION DATA

Color: White and Custom Colors

Finish: High-gloss

Clean up solvent: Mineral Spirits

Density: 10.00 lbs/gal

VOC: 1.32 lbs/gal (158 g/L)

Solids: Volume: 58 +/- 2%

Practical coverage: Apply at 380-500 sq ft/gal (9-12 m²/L) Actual coverage depending on type and structure of substrate and application method

Dry Time: 77°F (25°C) & 50% RH: To touch – 1 hour
To recoat – 4 hours



SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, rust scale, loose and flaking paint and other foreign substances.

NEW SURFACES

Wood - Prime with Camarol, use wood combination fillers to level surface imperfections. Sand accordingly. Finish using this product.

Steel - best results are obtained over a surface sandblasted to a Commercial Blast (SSPC-SP6). Performance over hand or power tool cleaned surfaces is dependent on the degree of cleaning. Prime with Camarol before applying this product.

Metal & aluminum - Prime galvanized metal or aluminum with a galvanized metal primer.

Concrete, Plaster and Masonry - Cure at least 30 days before painting. Ph must be 10.0 or lower. Poured concrete or pre-cast concrete needs chemical cleaning or a light sand blasting. Rinse completely with water and allow to fully dry. Remove loose aggregate and prime with Euro Fix Special primer/sealer. For concrete block, fill and level with a Euro Block Filler.

PREVIOUSLY PAINTED SURFACES

Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Dull glossy areas by light sanding. Remove sanding dust. Remove loose or peeling paint to sound surface by high pressure water cleaning. Remove all mildew by washing with a solution of 16 oz (473 mL) liquid household bleach and two oz (59 mL) non-ammoniated liquid detergent per gallon (3.785 L) of water. Rinse surface clean with water and allow to dry. Prime with Euro Fix Special.

DIRECTIONS FOR USE

Tools - May be applied by brush, roller or spray. For airless spray use a 0.13" tip. Adjust pressure as needed. Do not apply in damp weather or when surface or air temperature is below 4°C (40°F)

Painting & Cleaning - Provide good ventilation and warmth for normal drying. Two coats will provide best durability and uniformity. Clean up with mineral spirits.

SHIPPING

Freight Classification:
Paint, Combustible Liquid

Packaging: 1 gallon (3.785L)
1 quart (0.946L)

Flash Point: 40°C (104°F)

LIMITATIONS OF LIABILITY

The information in this data sheet is based on laboratory tests we believe to be accurate and is intended for guidance purposes only. All recommendations or suggestions relating to the use of the products made by Caribbean Paint Factory Aruba, whether in technical documentation, in response to a specific inquiry, or otherwise, are based on data which, to the best of our knowledge, are reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and it is the end user's responsibility to determine the suitability of the product for its intended use. Caribbean Paint Factory Aruba has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Caribbean Paint Factory does therefore not accept liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product. The English text of this document shall prevail over any translation thereof.

