



DESCRIPTION

Euro Floor Coating is designed to withstand foot and regular traffic. It can be used on interior or exterior wood and concrete floors. This versatile coating is not only used for stairs, porches, railings, steps, garage floors, and decks but also for decorative purposes on properly prepared steel structures.

FEATURES

- ▶ Durable semi-gloss finish
- ▶ Fast Drying
- ▶ Good resistance to oil, grease and water
- ▶ Good color and gloss retention
- ▶ Excellent adhesion
- ▶ Excellent wash ability

COMPOSITION

- ▶ 100% Acrylic Resin
 - ▶ Titanium Dioxide and extender pigments
- Not manufactured with lead or chromate containing materials

SPECIFICATION DATA

Color: White & Custom Colors

Finish: Semi-gloss

Clean up solvent: Mineral Spirits

Density: 10.00 lbs/gal (1.20 kg/L)

VOC: 1.20 lbs/gal (144 g/L)

Solids: Volume: 52 +/- 2%

Practical coverage: Apply at 400-500 sq ft/gal (10-12 m²/L) Actual coverage depending on type and structure of substrate and application method

Dry Time: 77°F (25°C) & 50% RH: To touch – ½ hour. To recoat – Overnight



SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, grease, dirt, mildew, form release agents, curing compounds, loose and flaking paint and other foreign substances.

NEW SURFACES

Concrete (concrete floors) and Masonry – Do not use on floors subject to dampness from the ground. Cure at least 30 days before painting. Poured concrete or pre-cast concrete needs chemical cleaning or a light sand blasting. Rinse completely with water and allow to fully dry. Remove loose aggregate and prime with this product primer/sealer. For concrete block, fill and level with a Euro Block Filler.

Wood - Prime with this product, use wood combination fillers to level surface imperfections. Sand accordingly. Apply finish using this product.

Steel – best results are obtained over a surface sandblasted to a Commercial Blast (SSPC-SP6). Performance over hand or power tool cleaned surfaces is dependent on the degree of cleaning.

Metal & aluminum – Prime galvanized metal or aluminum with a galvanized metal primer.

PREVIOUSLY PAINTED SURFACES

Wash to remove contaminants. Rinse thoroughly with water and allow to dry. Dull glossy areas by light sanding. Remove sanding dust. Remove loose or peeling paint to sound surface by high pressure water cleaning. Remove all mildew by washing with a solution of 16 oz (473 mL) liquid household bleach and two oz (59 mL) non-ammoniated liquid detergent per gallon (3.785 L) of water. Rinse surface clean with water and allow to dry. Prime with this product.

DIRECTIONS FOR USE

Tools – May be applied by brush, roller or spray. For airless spray use a 0.13" tip. Adjust pressure as needed. Do not apply in damp weather or when surface or air temperature is below 4°C (40°F)

Painting & Cleaning – Provide good ventilation and warmth for normal drying. Two coats will provide best durability and uniformity. Clean up with mineral spirits.

SHIPPING

Freight Classification:
Paint, Combustible Liquid

Packaging: 1 gallon (3.785L)

Flash Point: None

LIMITATIONS OF LIABILITY

The information in this data sheet is based on laboratory tests we believe to be accurate and is intended for guidance purposes only. All recommendations or suggestions relating to the use of the products made by Caribbean Paint Factory Aruba, whether in technical documentation, in response to a specific inquiry, or otherwise, are based on data which, to the best of our knowledge, are reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and it is the end user's responsibility to determine the suitability of the product for its intended use. Caribbean Paint Factory Aruba has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Caribbean Paint Factory does therefore not accept liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product. The English text of this document shall prevail over any translation thereof.

