



## DESCRIPTION

EURO ACRYL exterior satin is an ideal finish for asbestos, eternit, and fiber cement roofing. It is also used as a finishing coat on concrete, stucco, masonry, and wallboard. Formulated with 100% acrylic to protect against UV rays, color fading, and severe weather conditions.

## FEATURES

- ▶ Resists dirt
- ▶ Very good hiding power
- ▶ Provides a mildew resistant coating
- ▶ Water vapor permeable
- ▶ Durable and washable
- ▶ Odorless

## COMPOSITION

- ▶ 100% Acrylic Resin
  - ▶ Titanium Dioxide and extender pigments
- Not manufactured with lead or chromate containing materials

## SPECIFICATION DATA

**Color:** Dark custom colors

**Finish:** Satin

**Clean up solvent:** Tap water

**Density:** 1.5 g/cm<sup>3</sup>

**VOC:** 0.24 lbs/gal (29 g/L)

**Solids:** Volume: 36 +/- 2%

**Practical coverage:** Apply at 300-400 sq ft/gal (7-10 m<sup>2</sup>/L) Actual coverage depending on type and structure of substrate and application method

**Dry Time:** 77°F (25°C) & 50% RH: To touch – 1 hour.  
To recoat – 4 hours



## SURFACE PREPARATION

Fill and level all holes, cracks or open joints with paintable caulk. All areas should be clean, sound and free of flaking paint or any substances such as oil, grease and dirt. Prepare previously painted surfaces with this product or Euro Fix Special primer/sealer

### NEW SURFACES

**Wood** - Sand to a smooth surface, then prime wood with Camarol Alkyd primer. Surface can be finished with this product.

**Concrete, Plaster and Masonry** - Cure for 30 days before painting. Poured concrete or pre-cast concrete needs chemical cleaning or a light sand blasting. Rinse completely with water and allow to fully dry. Remove loose aggregate and prime with this product or Euro Fix Special primer/sealer. For concrete block, fill and level with a Euro Block Filler.

**Steel, galvanized metal and aluminum** - Clean off oils, then prime with Euro Metal Primer

## DIRECTIONS FOR USE

**Tools** - Use a 1/2" or larger nap roller [lambswool rollers recommended for the professional] and a quality brush. May also be applied using airless spray equipment with a .015" to 0.017" tip at 2000 – 2500 psi pressure.

**Painting & Cleaning** – No thinning required for roller applications. Thinning allowed with water (0-10%) if necessary only when using a sprayer. Do not paint if rain, snow, heavy dew or lower temperatures are expected within two hours of painting. Dampen roller slightly with water. Clean hands and tools with warm water. Clean spills right away with a damp cloth.

## SHIPPING

**Freight Classification:**  
Paint, Freezable

**Packaging:** 1 gallon (3.785L)  
5 gallon (18.925L)

**Flash Point:** None

## LIMITATIONS OF LIABILITY

The information in this data sheet is based on laboratory tests we believe to be accurate and is intended for guidance purposes only. All recommendations or suggestions relating to the use of the products made by Caribbean Paint Factory Aruba, whether in technical documentation, in response to a specific inquiry, or otherwise, are based on data which, to the best of our knowledge, are reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and it is the end user's responsibility to determine the suitability of the product for its intended use. Caribbean Paint Factory Aruba has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Caribbean Paint Factory does therefore not accept liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues, and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product. The English text of this document shall prevail over any translation thereof.

